



TANO

C A B L E

河南泰诺电缆有限公司

HENAN TANO CABLE CO.,LTD.



AAC to ASTM B231/B231 M STANDARD



TANO

B L E

Henan Tano Cable Co., Ltd.(Tano Cable for short), is a leading and professional manufacturer of cable and wire with more than 20 years' history and manufacturing experience, located in Zhengzhou city which is the capital of Henan province, China.

Tano Cable aims at providing integral power solution for international customers. We are working together as one company to provide products and technologies for building, maintaining and advancing the power and information infrastructures that connect the world. We mainly have the following products with strong competitiveness: All Aluminum Conductors (AAC), All Aluminum Alloy Conductors (AAAC), Aluminum Conductors Steel Reinforcement (ACSR) , Aerial Bundled Cables (ABC), building wire, welding cable, control cable, instrument cable, rubber cable, PVC insulated power cable, XLPE insulated power cable up to 500KV, customer-tailored cable and cable accessories, conforming to many different Country or international standard, such as IEC, HAR, BS, DIN, ICEA, ASTM, SABS, AS/NZS, JIS and so on.

Tano Cable pays great importance on the quality. We have strong teams and equipments for both production and inspection. Moreover, we have been awarded many certificates of ISO, CE, SONCAP, others from China and abroad. We keep improving our quality management system to meet the client's final satisfaction.

C A B L E

Tano Cable has provided services to the global clients who working in all areas of the energy, construction, industrial, specialty and communications market, and obtained the client's trust and compliment.

Welcome your any inquiry! Welcome your any visit! Welcome your any contact! We will take our biggest sincerity to be your long-term friend and partner.





All Aluminum Conductor (AAC) Cables to ASTM B231/B231M Standard

APPLICATION

AAC conductor is also known as aluminium stranded conductor. It is manufactured from electrolytically refined aluminium, with a minimum purity of 99.7%.

STANDARD

Basic design to ASTM B231/ B231M standard.

CONSTRUCTION

Concentric lay stranded Aluminium Conductor (AAC) is made up of one or more strands of hard drawn 1350 aluminum alloy. These conductors are used in low, medium and high voltage overhead lines. AAC has seen extensive use in urban areas where spans are usually short but high conductivity is required. The excellent corrosion resistance of aluminium has made AAC a conductor of choice in coastal areas. Because of its relatively poor strength to weight ratio, AAC had limited use in transmission lines and rural distribution because of long spans utilized. All aluminium conductors are made up of one or more strands of aluminium wire dep.

ELECTRICAL PROPERTIES

Density@20°C	2.703 kg/dm
Temperature Coefficient@20°C	0.00403 (°C)
Resistivity@20°C	0.028264
Linear Expansivity	23 x10 (°C)-6

SERVICE CONDITIONS

Ambient Temperature	-5°C - 50°C
Wind Pressure	80 - 130kg/m ²
Seismic Acceleration	0.12 - 0.05g
Isokeraunic Level	10 - 18
Relative Humidity	5 - 100%

CONSTRUCTION PARAMETER

Code	Nominal Area		Stranding	Overall Diameter	Weight	Rated Strength	Electrical Resistance	Current Rating*
	AWG&MCM	mm ²						
Peachbell	6	13.3	7/1.56	4.68	36.6	2.53	2.1477	75
Rose	4	21.1	7/1.96	5.88	58.2	3.91	1.3606	99
Irish	2	33.6	7/2.47	7.41	92.6	5.99	0.8567	132
Pansy	1	42.4	7/2.78	8.34	116.6	7.3	0.6763	153
Poppy	1/0.0	53.5	7/3.12	9.36	147.2	8.84	0.5369	176
Aster	2/0.0	67.4	7/3.50	10.5	185.7	11.1	0.4267	203
Phlox	3/0.0	85	7/3.93	11.79	233.9	13.5	0.3384	234
Oxlip	4/0.0	107.2	7/4.42	13.26	295.2	17	0.2675	270
Valerian	250	126.7	19/2.91	14.55	348.6	20.7	0.2274	299
Sneezewort	250	126.7	7/4.80	14.4	348.8	20.1	0.2269	299
Laurel	266.8	135.2	19/3.01	15.05	372.2	22.1	0.2125	312
Daisy	266.8	135.2	7/4.96	14.88	372.3	21.4	0.2125	311
Peony	300	152	19/3.19	15.95	418.3	24.3	0.1892	335
Tulip	336.4	170.5	19/3.38	16.9	469.5	27.3	0.1686	359
Daffodil	350	177.3	19/3.45	17.25	487.9	28.4	0.1618	369
Canna	397.5	201.4	19/3.67	18.35	554.9	31.6	0.143	397
Goldentuft	450	228	19/3.91	19.55	627.6	35	0.126	429
Syringa	477	241.7	37/2.88	20.16	664.8	38.6	0.1192	444
Cosmos	477	241.7	19/4.02	20.1	664.8	37	0.1192	444
Hyacinth	500	253.3	37/2.95	20.65	696.8	40.5	0.1136	458
Zinnia	500	253.3	19/4.12	20.6	697.1	38.9	0.1134	458
Dahlia	556.5	282	19/4.35	21.75	775.8	43.3	0.1018	489
Mistletoe	556.5	282	37/3.12	21.84	775.7	44.3	0.1016	490
Meadowsweet	600	304	37/3.23	22.61	836.3	47.5	0.0948	511
Orchid	636	322.3	37/3.33	23.31	886.9	50.4	0.0892	530
Heuchera	650	329.4	37/3.37	23.59	907.4	51.7	0.0871	538
Flag	700	354.7	61/2.72	24.48	975.8	57.1	0.0811	561
Verbena	700	354.7	37/3.49	24.43	975.7	55.4	0.0812	561
Nasturtium	715.5	362.6	61/2.75	24.75	998.5	58.4	0.0793	569
Violet	715.5	362.6	37/3.53	24.71	998.5	56.7	0.0794	568

Cattail	750	380	61/2.82	25.38	1046	60.3	0.0754	587
Petunia	750	380	37/3.62	25.34	1046	58.6	0.0755	586
Lilac	795	402.8	61/2.90	26.1	1110	63.8	0.0713	607
Arbutus	795	402.8	37/3.72	26.04	1109	61.8	0.0715	605
Snapdragon	900	456	61/3.09	27.81	1256	70.8	0.0628	654
Cockscomb	900	456	37/3.96	27.72	1256	68.4	0.0631	652
Goldenrod	954	483.4	61/3.18	28.62	1331	75	0.0593	677
Magnolia	954	483.4	37/4.08	28.56	1331	72.6	0.0594	676
Carmellia	1000	506.7	61/3.25	29.25	1394	78.3	0.0568	695
Hawkweed	1000	506.7	37/4.18	29.26	1395	76.2	0.0566	696
Larkspur	1033.5	523.7	61/3.31	29.79	1442	81.3	0.0547	710
Bluebell	1033.5	523.7	37/4.25	29.75	1441	78.8	0.0547	710
Marigold	1113	564	61/3.43	30.87	1553	87.3	0.051	740
Hawthorn	1192.5	604.2	61/3.55	31.95	1662	93.5	0.0476	771
Narsissus	1272	644.5	61/3.67	33.03	1774	98.1	0.0445	802
Columbine	1351	694.8	61/3.78	34.02	1884	104	0.042	829
Carnation	1431	725.1	61/3.89	35.01	1997	108	0.0396	858
Gladiolus	1510.5	765.4	61/4.00	36	2108	114	0.0375	885
Coreopsis	1590	805.7	61/4.10	36.9	2216	120	0.0357	911
Gladiolus	1510.5	765.4	61/4.00	36	2108	114	0.0375	885
Coreopsis	1590	805.7	61/4.10	36.9	2216	120	0.0357	911
Jassamine	1750	886.7	61/4.30	38.7	2442	132	0.0324	962
Cowslip*	2000	1013	91/3.77	41.47	2787	153	0.0286	1032
Sagebrush*	2250	1140	91/3.99	43.89	3166	167	0.0255	1099
Lupine*	2500	1267	91/4.21	46.31	3519	186	0.0229	1163
Bitterrot*	2750	1393	91/4.42	48.62	3872	205	0.0208	1223
Trillium*	3000	1520	127/3.90	50.7	4226	223	0.0193	1271
Bluebonnet*	3500	1773	127/4.22	54.86	4977	261	0.0165	1373

(*) Note: The values of current rating mentioned in above Table are based on wind velocity of 0.6 metre/second, solar heat radiation of 1200 watt/metre², ambient temperature of 50° C & conductor temperature of 80°C.

TECHNICAL DATA

Numbers of Wires	Final modulus of Elasticity		Coefficient of Linear Expansion	
	Kg/mm ²	lb/in ²	1/C°	1/F°
7	6000	8.5 x10 ⁶	23.0 x10 ⁻⁶	112.8 x10 ⁻⁶
19	5700	8.1 x10 ⁶	23.0 x10 ⁻⁶	112.8 x10 ⁻⁶
37	5700	8.1 x10 ⁶	23.0 x10 ⁻⁶	112.8 x10 ⁻⁶
61	5500	7.8 x10 ⁶	23.0 x10 ⁻⁶	112.8 x10 ⁻⁶
91	5500	7.8 x10 ⁶	23.0 x10 ⁻⁶	112.8 x10 ⁻⁶



河南泰诺电缆有限公司
HENAN TANO CABLE CO.,LTD.

Website: <http://www.tanocable.com/>

Tel.: 0086-371-60306197

Fax: 0086-371-60306197

Email: info@tanocable.com

Address: Zhengzhou City, Henan
Province, China.

Zip: 450000