



TANO

C A B L E

河南泰诺电缆有限公司

HENAN TANO CABLE CO.,LTD.



AAC to BS 215-1 STANDARD



TANO

B L E

Henan Tano Cable Co., Ltd.(Tano Cable for short), is a leading and professional manufacturer of cable and wire with more than 20 years' history and manufacturing experience, located in Zhengzhou city which is the capital of Henan province, China.

Tano Cable aims at providing integral power solution for international customers. We are working together as one company to provide products and technologies for building, maintaining and advancing the power and information infrastructures that connect the world. We mainly have the following products with strong competitiveness: All Aluminum Conductors (AAC), All Aluminum Alloy Conductors (AAAC), Aluminum Conductors Steel Reinforcement (ACSR) , Aerial Bundled Cables (ABC), building wire, welding cable, control cable, instrument cable, rubber cable, PVC insulated power cable, XLPE insulated power cable up to 500KV, customer-tailored cable and cable accessories, conforming to many different Country or international standard, such as IEC, HAR, BS, DIN, ICEA, ASTM, SABS, AS/NZS, JIS and so on.

Tano Cable pays great importance on the quality. We have strong teams and equipments for both production and inspection. Moreover, we have been awarded many certificates of ISO, CE, SONCAP, others from China and abroad. We keep improving our quality management system to meet the client's final satisfaction.

Tano Cable has provided services to the global clients who working in all areas of the energy, construction, industrial, specialty and communications market, and obtained the client's trust and compliment.

Welcome your any inquiry! Welcome your any visit! Welcome your any contact! We will take our biggest sincerity to be your long-term friend and partner.





All Aluminum Conductor (AAC) Cables to BS 215-1 Standard

APPLICATION

AAC conductor is also known as aluminium stranded conductor. It is manufactured from electrolytically refined aluminium, with a minimum purity of 99.7%.

STANDARD

Basic design to BS 215-1 standard.

CONSTRUCTION

Concentric lay stranded Aluminium Conductor (AAC) is made up of one or more strands of hard drawn 1350 aluminum alloy. These conductors are used in low, medium and high voltage overhead lines. AAC has seen extensive use in urban areas where spans are usually short but high conductivity is required. The excellent corrosion resistance of aluminium has made AAC a conductor of choice in coastal areas. Because of its relatively poor strength to weight ratio, AAC had limited use in transmission lines and rural distribution because of long spans utilized. All aluminium conductors are made up of one or more strands of aluminium wire dep.

ELECTRICAL PROPERTIES

Density@20°C	2.703 kg/dm
Temperature Coefficient@20°C	0.00403 (°C)
Resistivity@20°C	0.028264
Linear Expansivity	23 x10 (°C)-6

SERVICE CONDITIONS

Ambient Temperature	-5°C - 50°C
Wind Pressure	80 – 130kg/m ²
Seismic Acceleration	0.12 - 0.05g
Isokeraunic Level	10 – 18
Relative Humidity	5 – 100%

CONSTRUCTION PARAMETER

Code	Nominal Area		Stranding	Overall Diameter	Weight	Rated Strength	Electrical Resistance	Current Rating*
	Nominal	Calculated						
	mm ²	mm ²	No. x mm	mm	kg/km	KN	Ω/km	A
Midge	22	23.33	7/2.06	6.18	64	3.99	1.227	106
Gnat	25	26.8	7/2.21	6.6	73.8	4.83	1.0643	122
Mosquito	35	37	7/2.59	7.8	102.1	6.27	0.7749	141
Ladybird	40	42.8	7/2.79	8.4	117.9	7.28	0.6678	157
Ant	50	52.83	7/3.1	9.3	145	8.28	0.5419	175
Fly	60	63.55	7/3.4	10.2	174	9.9	0.4505	196
Wasp	100	106	7/4.39	13.17	290	16	0.2702	268
Hornet	150	157.6	19/3.25	16.25	434	25.7	0.1825	342
Charler	200	213.2	19/3.78	18.9	587	35.4	0.1349	412
Cockroach	250	265.7	19/4.22	21.1	731	40.4	0.1083	471
Butterfly	300	322.7	19/4.65	23.25	888	48.75	0.08916	530
Centipede	400	415.2	37/3.78	26.46	1145	63.1	0.06944	616
Maybug	475	486.1	37/4.09	28.6	1342	0.05571	0.05900	740
Skorpion	500	529.8	37/4.27	29.9	1460	0.04916	0.05400	887
Cicada	600	628.3	37/4.65	32.6	1733	0.03423	0.04500	1056

(*) Note: The values of current rating mentioned in above Table are based on wind velocity of 0.6 metre/second, solar heat radiation of 1200 watt/metre², ambient temperature of 50° C & conductor temperature of 80°C.

TECHNICAL DATA

Numbers of Wires	Final modulus of Elasticity		Coefficient of Linear Expansion	
	Kg/mm ²	lb/in ²	1/C°	1/F°
7	6000	8.5 x10 ⁶	23.0 x10 ⁻⁴	112.8 x10 ⁻⁴
19	5700	8.1 x10 ⁶	23.0 x10 ⁻⁴	112.8 x10 ⁻⁴
37	5700	8.1 x10 ⁶	23.0 x10 ⁻⁴	112.8 x10 ⁻⁴
61	5500	7.8 x10 ⁶	23.0 x10 ⁻⁴	112.8 x10 ⁻⁴
91	5500	7.8 x10 ⁶	23.0 x10 ⁻⁴	112.8 x10 ⁻⁴



河南泰诺电缆有限公司
HENAN TANO CABLE CO.,LTD.

Website: <http://www.tanocable.com/>

Tel.: 0086-371-60306197

Fax: 0086-371-60306197

Email: info@tanocable.com

Address: Zhengzhou City, Henan
Province, China.

Zip: 450000